

## Belægning Tix

Wax/bitumen-based anti-corrosion

Black, thick, thixotropic, wax/bitumen-based anti-corrosion product that leaves a strong, durable, solid, and flexible coating.

### Range of application:

This product is intended for use on vehicle underbodies, wheel arches, chassis frames, and other areas subject to significant wear. A primer—such as SUVO 216, Rust Stop 80, or Rust Stop 150—must always be applied prior to the application of this product.

### Package

01-914 / 5-lit can  
01-913 / 10-lit can  
01-912 / 25-lit can  
01-911 / 60-lit drum  
01-910 / 208-lit drum

### Instructions for use:

Apply using a high-pressure system or brush. Before application, the surface must be dry and free of loose flakes and dirt. Belægning TIX can be applied wet-on-wet.

Technical data	
Color:	Black
Consistency:	Thixotropic
Type of film:	Strong bitumen/wax surface
Density:	900 – 1100 mPas
Dry content:	60 – 70%
Volatiles solvents:	30 – 40%
Film thickness:	200 – 250 µm wet film
Application temperature:	20 – 25° C
Removal with:	Clairsolrens, Clearrens or LHG Rensevæske
Drying time:	24 hours at 23° C
Storing temperature:	5 – 25° C

For further information we recommend the safety data sheet or instruction on package.